



**BUREAU
VERITAS**

TEST REPORT

LAB NO.: (6621)105-0625
FORM NO.: /
DATE IN: Apr 15, 2021
DATE OUT: Apr 21, 2021
NO. OF WORKING DAYS: 5
PAGE 1 OF 3

OVERALL RATING

PASS	<u> X </u>
FAIL	<u> </u>
DATA	<u> </u>

Vendor:	WUHAN YOUFU INTERNATIONAL TRADE CO.,LTD	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	/
Sample Description:	AAMI PP + PE ISOLATION GOWN LEVEL 1	Style Description:	/
Color:	BLUE	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	/
SKU:	/		

Product Category	/
Test Requested	PARTIAL TEST
Previous Report No.	/

Submitted Fiber Content	70% PP + 30% PE
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
WATER RESISTANCE: IMPACT PENETRATION TEST	X			

Remark: [BVCPS \(Shanghai\) contact information for this report](#)

Address: [No.168, Guanghua Road, Zhuangqiao Town, Minhang, Shanghai, China.](#)

General Information:

Jojo Li 086-021-24081666*9309, email: jojo-wj.li@cn.bureauveritas.com
Noah Zhang 086-021-24081666*1720, email: Xiaoliang.zhang@cn.bureauveritas.com
Seven Sun 086-021-24081666*9327, email: Seven.sun@cn.bureauveritas.com
Du Shuang 086-021-24081666*1709, email: shuang.du@cn.bureauveritas.com
Challenge Qiao 086-021-24081666*9331, email: challenge.qiao@cn.bureauveritas.com
Lizzy Liao 086-021-24081666*9303, email: lizzy.liao@bureauveritas.com
Sherry Shen 086-021-24081666*9310, email: shirley-ll.shen@cn.bureauveritas.com

Technical Questions:

Pat Liu 086-021-24081745, email: Pat.liu@cn.bureauveritas.com
Rio Zhang 86-21-24081666*9305, email: Rio.Zhang@cn.bureauveritas.com

BUREAU VERITAS
CONSUMER PRODUCTS SERVICES (SHANGHAI)



JULIA YAN
PROGRAM MANAGER

<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>				<u>REQUIREMENTS</u>
<u>WATER RESISTANCE: IMPACT PENETRATION TEST</u> (AATCC 42-17)					
	1	2	3	AVERAGE	
FABRIC (GRAM)	0.0	0.0	0.0	0.0	MAX. 4.5 GRAM
SHOULDER (GRAM)			0.4		MAX. 4.5 GRAM
ARM OPENING (GRAM)			0.2		MAX. 4.5 GRAM
SLEEVE (GRAM)			0.1		MAX. 4.5 GRAM
BELT (GRAM)			0.2		MAX. 4.5 GRAM



END OF REPORT