



TEST REPORT

LAB NO.: (6621)125-0106
FORM NO.: /
DATE IN: May 05, 2021
DATE OUT: May 10, 2021
NO. OF WORKING DAYS: 4
PAGE 1 OF 3

<u>OVERALL RATING</u>	
PASS	_____X_____
FAIL	_____
DATA	_____

Vendor:	WUHAN YOUFU INTERNATIONAL TRADE CO LTD	Agent:	/
Fabric Supplier/Mill:	/	Factory/Manufacturer:	/
P.O. No.:	/	Style No.:	/
Sample Description:	AAMI LEVEL 2 CPE ISOLATION GOWN AAMI LEVEL 3 CPE ISOLATION GOWN	Style Description:	/
Color:	BLUE	Country of Origin:	/
Claimed Fabric Weight:	/	Claimed Fabric Count:	/
Yarn Size:	/	Submitted Size:	/
Size Range:	/	FPU No.:	/
GPU No.:	/	End Use:	ISOLATION
SKU:	/		

Product Category	/
Test Requested	/
Previous Report No.	/

Submitted Fiber Content	100% POLYETHYLENE
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
WATER RESISTANCE: IMPACT PENETRATION TEST	X			
WATER RESISTANCE: HYDROSTATIC PRESSURE TEST	X			

Remark: [BVCPS \(Shanghai\) contact information for this report](#)

Address: [No.168, Guanghua Road, Zhuangqiao Town, Minhang, Shanghai, China.](#)


General Information:

Jojo Li 086-021-24081666*9309, email: jojo-wj.li@cn.bureauveritas.com
Noah Zhang 086-021-24081666*9307, email: Xiaoliang.zhang@cn.bureauveritas.com
Seven Sun 086-021-24081666*9327, email: Seven.sun@cn.bureauveritas.com
Du Shuang 086-021-24081709, email: shuang.du@cn.bureauveritas.com
Challenge Qiao 086-021-24081666*9331, email: challenge.qiao@cn.bureauveritas.com
Lizzy Liao 086-021-24081666*9303, email: lizzy.liao@bureauveritas.com

Technical Questions:

Pat Liu 086-021-24081745, email: Pat.liu@cn.bureauveritas.com

BUREAU VERITAS
CONSUMER PRODUCTS SERVICES (SHANGHAI)



PAT LIU
PROGRAM MANAGER

<u>TEST PROPERTY</u>	<u>TEST RESULTS</u>				<u>REQUIREMENTS</u>
<u>WATER RESISTANCE: IMPACT TEST</u> (AATCC 42-17)					
	1	2	3	AVG.	
FABRIC (GRAM)	0.0	0.0	0.0	0.0	MAX. 1.0 GRAM
SLEEVE (GRAM)			0.0		MAX. 1.0 GRAM
<u>WATER RESISTANCE: HYDROSTATIC PRESSURE TEST</u> (AATCC 127)					
	1	2	3	AVG.	
FABRIC (CMH2O)	86.2	81.7	81.1	83.0	MIN. 50 CMH2O
SLEEVE (CMH2O)			85.5		MIN. 50 CMH2O



END OF REPORT