





## TEST REPORT

(Electronic version)

扫码下载报告

回数



VERIFICATION WEBSITE: www.gttc.net.cn VERIFICATION CODE: XLBH-4640-24

ISSUE DATE: 2020-11-09

WUHAN YOUFU INTERNATIONAL TRADE CO., LTD APPLICANT:

ADDRESS: ROOM3, 18/F, BUILDING S-1, KAILEGUIYUAN, NO. 108, ZHUODAOQUAN ROAD, HONGSHAN

DISTRICT, WUHAN CITY, HUBEI PROVINCE

INFORMATION CONFIRMED BY APPLICANT:

DISPOSABLE FACE MASK (NON MEDICAL USE)

QUANTITY: 100 PIECES

No: 200342194

STANDARD ADOPTED:

T/CNTAC 55-2020, T/CNITA 09104-2020 <Civil sanitary mask>

DATE RECEIVED/DATE TEST STARTED: 2020-11-02

CONCLUSION:

BACTERIAL FILTRATION EFFICIENCY M PARTICLE FILTRATION EFFICIENCY M AIRFLOW RESISTANCE M BREAKING STRENGTH OF JUNCTION BETWEEN MASK STRING AND MASK BODY

"M" -MEET THE STANDARD'S REQUIREMENT
"---" -NO COMMENT "F" -FAIL TO MEET THE STANDARD'S REQUIREMENT NOTE:

REMARK:

THIS REPORT IS THE ENGLISH TRANSLATION VERSION OF THE REPORT 200342193.

THE DECISION INDICATORS ARE DERIVED FROM THE GROUP STANDARD REQUIRED BY CLIENT (T/CNTAC 55-2020, T/CNTA 09104-2020). OUR INSPECTION CAPACITY AUTHORIZED BY CMA COVERS THE INSPECTION ITEMS T/CNTAC 55-2020, T/CNITA 09104-2020.

ALL THE TESTED ITEMS ARE TESTED UNDER THE STANDARD CONDITION (EXCEPT FOR INDICATION). COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.

THE EXPERIMENT WAS CARRIED OUT AT No. 1, ZHUJIANG ROAD, PANYU DISTRICT, GUANGZHOU, GUANGDONG, P. R. CHINA.

APPROVED BY:

Yuan Liu ENGINEER





总部:广州市番禺区珠江路1号 花都实验室:广州市花都区狮岭镇旗岭河滨西路1号 电话:020-61994598/61994599 电话:020-37721161/66348638







## TEST REPORT

(Electronic version)

No:200342194





总部:广州市番禺区珠江路1号 化都实验室:广州市花都区狮岭镇旗岭河渡西路1号 电话:020-61994598/61994599 电话:020-37721161/66348638







## TEST REPORT

(Electronic version)

No: 200342194

BACTERIAL FILTRATION EFFICIENCY (%)

M

(YY 0469-2011 ANNEX B, TEST BACTERIA: STAPHYLOCOCCUS AUREUS ATCC 6538, TEST AREA:  $49\text{cm}^2$ , FLOW RATE: 28.3L/min, MEAN PARTICLE SIZE: 3.0  $\mu$ m, RESULT OF THE POSITIVE CONTROL: 1.9 $\times10^3$  CFU, RESULT OF THE NEGATIVE CONTROL: <1CFU)

REQUIREMENT

 $E_1$  99. 3  $\geqslant 95$ 

BFE<sub>2</sub> 99. 2 (T/CNTAC 55-2020, T/CNITA 09104-2020)

BFE<sub>1</sub> 99.3 BFE<sub>2</sub> 99.2 BFE<sub>3</sub> 99.2

PARTICLE FILTRATION EFFICIENCY (%)

M

(YY 0469-2011 5.6.2, AIR FLOW: 30L/min, AEROSOL: NaCl, AEROSOL CONCENTRATION:

 $15 \text{mg/m}^3$  , TEMP:  $21.9 \,^{\circ}\text{C}$  , RH: 38.6 %

REQUIREMENT

MINIMUM 96.42 ≥90

(T/CNTAC 55-2020, T/CNITA 09104-2020)

AIRFLOW RESISTANCE (Pa)

M

(YY 0469-2011 5.6.2, AIR FLOW: 30L/min, AEROSOL: NaCl, AEROSOL CONCENTRATION:

 $15 \text{mg/m}^3$  , TEMP: 21.9°C, RH: 38.6%)

REQUIREMENT

MAXIMUM 47.9

≤49 (T/CNTAC 55-2020, T/CNITA 09104-2020)

BREAKING STRENGTH OF JUNCTION BETWEEN MASK STRING AND MASK BODY (N)

M

(GB/T 13773. 2-2008)

(GB/T 13773.2-2008 idt ISO 13935-2:1999)

REQUIREMENT

 $\geq 5$ 

10

(T/CNTAC 55-2020, T/CNITA 09104-2020)

A 验检测专用章 (GF2) PAGE 3 OF 3

——End of Report——